



Flowfresh SR (3-4 mm)



Standard Colour Chart



Buff



Cream



Mustard



Red



Green



Grey

The applied colours may differ slightly from the examples shown above.
Contact our customer services for a true colour sample or a special colour match.

Description

Flowfresh SR is a heavy duty, chemical resistant, antimicrobial polyurethane resin floor system with a positively textured finish. Flowfresh SR incorporates Polygiene® - a performance based antimicrobial which inhibits the growth of bacteria, fungi, moulds and mildew.

Typical Uses

Ideal for wet processing zones such as food manufacturing, preparation areas and chemical processing plants.


Benefits

- Proven antimicrobial performance
- High chemical resistance
- Easy to clean and sterilise
- Textured anti-slip surface
- Heat resistant to 90 °C
- Freeze/thaw resistant
- Non-tainting
- High abrasion resistance
- Withstands high mechanical stress
- Low odour during application
- Fast return to service
- UV light stable grade is available

Project References

B.Foods, Saha Farms, CP Foods, Sun Valley Foods, Nestlé, Malee Sompran, Thai International Airways, Panus Poultry, Fonterra Dairies

System Design



Model Specification

Product: Flowfresh SR
Finish: Gloss/Matt/Textured
Thickness: 3-4mm
Colour: _____

Preparatory work and application in accordance with manufacturer's instructions.

Manufacturer: Flowcrete Asia Sdn Bhd
Telephone : Customer Service - +603 6277 9575

Substrate Requirements

Concrete or screed substrate should be a minimum of 25N/ mm², free from laitance, dust and other contamination. The substrate should be surface dry and free from rising damp and ground water pressure.

Products Included in this System

Flowprime
Flowfresh MF/Flowfresh SL
Anti-slip aggregate
Flowfresh Coating
Flowfresh/ Flowseal UV

Detailed application instructions are available upon request.

Installation Service

The installation should be carried out by a Flowcrete approved applicator with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our web site at www.flowcreteaustralia.com.au.

Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

Focus on the Floorzone

Flowcrete Asia Sdn Bhd is a division of the Flowcrete Group, world leaders in specialist industrial and commercial flooring. Systems available include: underfloor heating systems, floor screeds, surface damp proof membranes, decorative floor finishes, seamless terrazzo, car park deck waterproofing and corrosion protection systems... to name just a few. Our corporate objective is to satisfy your flooring needs.

Microbial / Fungal Resistance

The Polygiene® antimicrobial additive incorporated into Flowfresh SR provides control of most bacteria and fungi which come into contact with the floor.

Colour Stability

Flowfresh SR is not colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in light colours and blues but does not compromise the product's chemical resistance or physical characteristics. Consult our Technical Department for UV light stable specification.

Technical Information

The figures that follow are typical properties achieved in laboratory tests at 20 °C and at 50% Relative Humidity.

Fire Resistance	BS476:Part 7 Surface Spread of Flame: Class 2 (indicative)
Slip Resistance	TRRL Pendulum Slip Test Dry 80 Wet min 45 (aggregate dependant)
Impact Resistance	BS8204 Part1 Cat: A (<0.5mm) ISO6272 1kg weight >1.8m 2kg weight >1.5m
Temperature Resistance	From -15°C to 90°C.
Water Permeability	Nil-Karsten T est (impermeable)
Vapour Permeability	ASTM E96:90 3g/m/24hrs (at 9mm thick)
Chemical Resistance	Contact Technical Department Excellent resistance to sugars and most acids (organic and inorganic)
Abrasion Resistance	Taber Abrader: 0.1g loss per 1000 cycles (1kg load using CS17 wheels)
Compressive Strength	60 N/mm ² (BS6319)
Flexural Strength	20 N/mm ² (BS6319)
Tensile Strength	10 N/mm ² (BS6319)
Bond Strength	Greater than cohesive strength of 25 N/mm ² concrete. >1.5 MPa.
Toxicity (when cured)	Taint Free to sensitive foodstuffs

Speed of Cure

	10 °C	20 °C	30 °C
Light traffic	36 hrs	24 hrs	12 hrs
Full traffic	72 hrs	48 hrs	24 hrs
Full chemical cure	12 days	7 days	6 days

Aftercare - Cleaning and Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Important Note

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

Further Information

To ensure you are specifying a fit for purpose flooring system for your project please consult our Technical Advisors on the number below or visit our website to register your interest in specifying one of the most durable floors on the market.

Flowcrete Australia Pty Ltd
Brisbane Office (Regional)
PO Box 817
Nundah QLD 4012
Tel: +61 7 3205 7115
Fax: +61 7 3205 3116
Email: australia@flowcrete.com
Flowcrete Australia is an RPM company

Sydney Office
Unit 4/24 Anzac Avenue
Smeaton Grange NSW 2567
Tel: +61 2 4648 0397
Fax: +61 2 4648 0719