AWTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Flowcrete Australia

Unit 2, 41 Deakin Street Brendale QLD 4500

Test Number :

18-001631

Issue Date

12/04/2018

Print Date

12/04/2018

Yes

Sample Description

Clients Ref:

Blistering

"Mondeco Rapide"

Resin & marble rigid panel adhered to FR cement sheet by client

Flooring, applied with trowel

Nominal Composition: Methyl Methacrylate Resin & Marble

Nominal Thickness: 8-10mm

AS/ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a **Radiant Heat Source**

Date of Sample Arrival 29/03/2018 **Date Tested** 09/04/2018 CHF Value 1 2 3 Mean Non Directional 64 64 44 5.7 k\///m² Smoke Value 3 1 Mean Non Directional <4 <4 <4 %.min

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

No directional properties, three specimens tested only.

Each specimen was clamped as supplied by client prior to testing.

125402 26635 Page 1 of 1

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Chemical Testing


Mechanical Testing

Performance & Approvals Testing

: Accreditation No

Accreditation No · Accreditation No.

983 1356





A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY