

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Flowcrete A Unit 2, 41 D Brendale Ql	eakin Street		Test Numb Issue Date Print Date	er: :	17-00155 24/04/20 21/05/201	17
Sample Description	Clients Ref : "Flowfast SR/SR Coated cement sheet Colour : Brown End Use : Roller/Trowell/Squee Nominal Composition : Methy Nominal Mass per Unit Area/Dens Nominal Thickness : 3mm	gee methacrylate/Sar				
S/ISO 9239.1-2003	Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source					
	Date of Sample Arrival		03/04/2017			
			03/04/2017 24/04/2017			
	Date of Sample Arrival	1		3	Mean	
	Date of Sample Arrival Date Tested	1 2.9	24/04/2017 2	3 3.0	Mean 2.9	kW/m²
	Date of Sample Arrival Date Tested CHF Value		24/04/2017 2			kW/m²
	Date of Sample Arrival Date Tested CHF Value Non Directional	2.9	24/04/2017 2 2.8	3.0	2.9	kW/m² %.min
	Date of Sample Arrival Date Tested CHF Value Non Directional Smoke Value	2.9 1	24/04/2017 2 2.8 2	3.0 3	2.9 Mean	
	Date of Sample Arrival Date Tested CHF Value Non Directional Smoke Value Non Directional	2.9 1 30	24/04/2017 2 2.8 2	3.0 3	2.9 Mean 26	

129831 18522 Page 1 of 2 Australian Wool testing Authority Ltd Copyright - All Rights Reserved Accredited for compliance with ISO/IEC 17025 - Chemical Testing : Accreditation No 983 Mechanical Testing : Accreditation No. 985 - Performance & Approvals Testing : Accreditation No 1356 Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd. SADM IA∉L A. JACKSON B.Sc.(Hons) MANAGING DIRECTOR APPROVED SIGNATORY

(C)

0204/11/06



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Flowcrete Australia Unit 2, 41 Deakin Street Brendale QLD 4500

 Test Number
 :
 17-001552

 Issue Date
 :
 24/04/2017

 Print Date
 :
 21/05/2018

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

No directional properties, three specimens tested only.

Each specimen was clamped as supplied by client prior to testing.

129831 Australian Wool testing Authority Ltd Copyright - All Rights Reserved

18522



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No. : Accreditation No.

983 985 1356

Page 2 of 2



0204/11/06

C

APPROVED SIGNATORY

SADY