

Project Details

Project Name	
System Name	Flowfresh SR 6mm (Gloss Finish)

Architectural Specification

Flowfresh SR


A chemical resistant, antimicrobial polyurethane resin floor coating containing Polygiene® with an positively textured gloss finish. Typically used in wet processing areas or food preparation zones.

Thickness	6mm	
Colour Choice		
Slip Resistance	P5 (Based on nominal 1mm sized Quartz Sand Aggregate)	
Fire Resistance AS/ISO 9239.1	CHF Value	10 kW/m ²
	Smoke Value	69% (Mean)
VOC Content ASTM D2369-10: 2015	< 140 g/L	
Antimicrobial	Polygiene®	
HACCP	HACCP International Certified	
Finish	Gloss	
Curing	Full Chemical Cure 7 Days @ 20°C	
Traffic	Vehicular Traffic 48hrs @ 20°C	
Manufacturer	Tremco CPG Australia Pty Ltd	
Address	63 Radley Street	
Suburb	Virginia	
State / Post Code	QLD 4014	
Main Telephone	+61 7 3205 7115	
Main Email	australia@flowcrete.com	
Key Contact		


Products Included In This System

Layer 1	Deckshield ED Primer / Flowfresh Primer *Only If Required for Porous Surfaces
Layer 2	Flowfresh SL Aggregate Scatter
Layer 3	Flowfresh Coating

System Design



Available Colours



The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from laitance, dust and other contamination. Substrate should be dry to 95% RH as per ASTM F2170 (AS1884:2012). Slab on ground concrete must have an effective damp proof membrane in place.

Surface Preparation

Concrete should be finished by steel trowel. Surface preparation is to be completed by totally enclosed shot blasting or coarse diamond grinding. All cementitious laitance must be removed to expose a sound substrate and provide a dry, dust free, open textured surface. All hard to reach areas and areas around the perimeter must be prepared using hand held preparation equipment.

Any damaged areas must be repaired with Flowtex F1 mortar. Consult Flowcrete prior to using an alternative repair mortar. Any rough or uneven areas must be made smooth with Flowcoat SC (Universal Resin Base A, Universal Hardener B, Sand/Silica Flour). Consult Flowcrete prior to using an alternative epoxy scratch coat.

Cleaning

For specific cleaning and maintenance requirements, please consult our Technical Advisory team on **07 3205 7115** or email australia@flowcrete.com.

Important

This specification assumes a concrete compressive strength greater than 25 N/mm², application and curing temperatures of 5–35°C, the presence of an effective damp proof membrane below substrate and concrete moisture content less than 95% RH. If moisture content is above 95% RH, please contact Flowcrete Australia.

This specification must be read in conjunction with relevant product technical data sheets and the application of all materials is to be strictly in accordance with manufacturer's instructions.

Note

When printed or saved externally, this document is uncontrolled and therefore may not be the latest version. Any recommendation or suggestion relating to the use of the products made by Tremco CPG Australia Pty Ltd., whether in its technical literature, or in response to a specific enquiry, or otherwise, is based upon data believed to be reliable, however the products and information are intended for use by Customers having requisite skill and know-how in the industry and therefore it is for the Customer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the Customer has done so at its sole discretion and risk.

This specification must be read in conjunction with relevant product technical data sheets and the application of all materials is to be strictly in accordance with manufacturer's instructions.