

# Deckcoat EP (0.4-1mm)

A car park deck coating system providing a colourful, watertight surface for intermediate decks of multi-storey structures.

Typically used to cosmetically enhance, reduce noise and brighten internal car parks.





## **Environmentally Friendly:** Low in Volatile Organic Compounds

(VOCs) and solvent free.



## Attractive:

Brightens up dull, dark and musty car park environments.



## Resistant:

Resistance to chemicals, fire and has a low slip potential.



## **Durable:**

Hard wearing, durable and abrasion resistant.

## **Technical Profile**

FIRE RESISTANCE	
EN 13505-1	B <sub>FL</sub> - s1
SLIP RESISTANCE	
Method described in AS4586-2013	Dry & Wet Rating is dependant on specification (in accordance with AS4586-2013)
The slipperiness of flooring materials can change significantly due to	

the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry).

Textured systems are recommended to meet slip resistance value requirements for wet conditions and/or surface contaminants (wet or dry) - please contact our Technical Advisors for further details

#### **TEMPERATURE RESISTANCE**

Tolerant up to 60°C

#### WATER PERMEABILITY

Karsten Test Nil (Impermeable)

#### **SURFACE HARDNESS**

Koenig Hardness Test 180secs

### **BOND STRENGTH**

ASTM D4541 (Pull-Off Test) >1.5MPa\*

#### ABRASION RESISTANCE

Taber Abrader BS8204-2

80mg loss per 1000 cycles 1kg load using CS10 wheels

Grade AR2

#### CHEMICAL RESISTANCE

Contact Technical Department

#### ENVIRONMENTALLY FRIENDLY

Green Label certified - 032-089 Environmentally Preferred Coating option available.

SPEED OF CURE**	10°C	20°C	30°C
Light Traffic	48 hrs	24 hrs	18 hrs
Full Traffic	72 hrs	48 hrs	36 hrs
Full Chemical Cure	12 days	7 days	6 days

These figures are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.


\*Assume concrete or substrate is a minimum of 25 N/mm².

#### **Model Specification**

System	Deckcoat EP
Finish	Textured
Thickness	Dependant on Specification
Manufacturer	Flowcrete
Contact	+61 7 3205 7115

Preparatory work and application in accordance wth manufacturer's instructions.

## System Design



## **Products Included In This System**

Layer 1	Deckcoat EP Primer	
	Deckshield Oxide / Quartz	
Layer 2	Deckcoat EP Topcoat	

### Coving

Coving forms an integral part of the flooring system. It creates a sealed finish between the floor and wall joint. Please refer to Flowtex F1 Coving Mortar for further information.

#### **Substrate Requirements**

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitence, dust and other contamination. Substrate should be dry to 75% RH as per AS1884-2012. Must be free from rising ground moisture or must have an effective DPM in place.

#### Installation Service

The installation should be carried out by a experienced contractor with a documented quality assurance scheme. For details of our recommended contractors, contact your local Flowcrete office. Detailed application instructions are available upon request.

#### **Environmental Considerations**

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs and maintenance. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained application teams.

## Aftercare, Cleaning & Maintenance

Please refer to Flowcrete Australia's current Cleaning and Maintenance Recommendations Guide.

### Warranty

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Warranty, Terms and Conditions of Sale', copies of which can be obtained on request. Warranty does not cover suitability, fit for purpose or any consequential or related damages. Please review warranty in detail before installing the products.

Version 1.0 [21/02/17]

Flowcrete Australia Pty Ltd
Unit 2 41 Deakin Street Brendale QLD 4500 Australia
Tel: +61 7 3205 7115 Fax: +61 7 3205 3116
Unit 1 12 Blackmore Road Smeaton Grange NSW 2567 Australia

Tel: +61 2 4648 0397 Fax: +61 2 4648 0719 Email: australia@flowcrete.com

N.B.

- 1. Light colours may require additional coats to achieve desired results.
- 2. Flowcrete assumes no responsibility for the application of incorrect colour.

  3. It is recommended that top coat colours match base coat colours to achieve desired results.
- 4. This product is not UV stable and will discolour unless otherwise stated.
- 5. Technical Data Sheet to be read in conjunction with Method Statements and Product Data Sheets.